


VdTÜV-Kennblatt for welding consumables

	1 Manufacturer/Supplier VDM Metals GmbH Plettenberger Straße 2 DEU 58791 Werdohl	2 No. of VdTÜV-Kennblatt: 07528.03 08.2014																
3 Welding consumable*: Schweißstab																		
4 Trade name*: VDM® FM 33																		
7 Type*: EN ISO 14343-A - S Z 33 32 1 Cu N L (1.4591)																		
11 Diameter range: 1,6 bis 3,0 mm																		
12 Auxiliary materials: EN ISO 14175 - I 1, R 1 (Ar + max 5% H2)																		
13 The validity of this Kennblatt will be certified, respectively, in the latest edition of CD-ROM TÜV-eignungsgeprüfte Schweißzusätze																		
15 Materials and postweld heat treatment																		
X 1 CrNiMoCuN 33 32 (1.4591) VdTÜV-Werkstoffblatt 516 sowie Mischverbindungen zwischen X 1 CrNiMoCuN 33 32 1 (1.4591) und Werkstoffen wie X 2 CrNiMo 18 10 (1.4583) Wärmebehandlung: U																		
16 Material groups acc. to CR ISO 15608																		
21 Root weldability: verified																		
23 Wall thickness: max. 20 mm																		
24 Type of current and polarity: G-																		
25 Welding position according to DIN ISO 6947: PA, PB, PC, PF																		
26 Highest operating temperature in the short-term range as for parent metal, but not higher than: 450°C																		
27 Highest operating temperature in the long-term range max.: --- °C																		
28 Lowest operating temperature/as for parent metal, but not lower than: -196°C																		
29 Design stress value/as for parent metal: wie Grundwerkstoff																		
30 For use in the long-term range: ---																		
31 Resistance to intergranular corrosion proven in accordance with: ---																		
32 Remarks: Prägung der Schweißstäbe: 1.4591 B Verformung des Schweißgutes max. 10%. Zu Wanddicke: Bei größeren (bis max. 40 mm) Wanddicken sind die Füllagen mit artfremden Schweißgut z. B. Nicrofer S 3028 zu schweißen und mindestens 2-lagig mit VDM® FM 33 abzudecken. Die speziellen Verarbeitungsrichtlinien des Schweißzusatzherstellers und des VdTÜV-Wbl. 516 sind zu beachten. Anforderungen an das Schweißgut, die bei der Eignungsprüfung abweichend vom Grundwerkstoff zu Grunde gelegt wurden: A5 >= 25%, Av >= 60 Joule (RT), Av >= 32 Joule (-196°C).																		
33 The approval test was done on the basis of VdTÜV-Merkblatt 1153. Where nothing different is said under the heading -Remarks-, this welding consumable is suitable provided Annex I Point 4 of the Pressure Equipment Directive 97/23/EC is observed.																		
34 Explanations <table border="0" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 25%;">A tempered</td> <td style="width: 25%;">S stress-relieved</td> <td style="width: 25%;">W soft annealed</td> <td style="width: 25%;">G+ direct current plus pole</td> </tr> <tr> <td>L solution annealed and quenched</td> <td>St stabilized</td> <td></td> <td>G- direct current minus pole</td> </tr> <tr> <td>N normalized</td> <td>U non-annealed</td> <td></td> <td>W alternating current</td> </tr> <tr> <td></td> <td>V hardened and tempered</td> <td></td> <td></td> </tr> </table>			A tempered	S stress-relieved	W soft annealed	G+ direct current plus pole	L solution annealed and quenched	St stabilized		G- direct current minus pole	N normalized	U non-annealed		W alternating current		V hardened and tempered		
A tempered	S stress-relieved	W soft annealed	G+ direct current plus pole															
L solution annealed and quenched	St stabilized		G- direct current minus pole															
N normalized	U non-annealed		W alternating current															
	V hardened and tempered																	
35 Compiled in accordance with the data of: TÜV NORD - Region Essen																		
The duplication, circulation, copy and complete edition by photomechanical or similar techniques remain subject to the editor's approval even if only used in extracts. Editor: Verband der TÜV e. V. Distribution: TÜV-Media GmbH, Am Grauen Stein, 51105 Köln - Unternehmensgruppe TÜV Rheinland Group																		

Dieses Kennblatt wurde mit Genehmigung des Herausgebers kostenlos durch die VDM Metals GmbH, 58762 Altena im Jahr 2022 zur Verfügung gestellt.

*) Statements of the manufacturer